

Transport Properties of $\text{Bi}_2\text{Sr}_{2-x}\text{La}_x\text{CaCu}_2\text{O}_{8+\delta}$ Single Crystals Grown by a Floating-Zone Method

Takenori Fujii^{1,2*} and Ichiro Terasaki^{1,2}.

¹*Department of Applied Physics,*

Waseda University, Tokyo 169-8555, Japan.

²*PREST, Japan Science and Technology Corporation,*
Kawaguchi 332-0012, JAPAN.

(Dated: February 2, 2008)

A parent insulator of the Bi-based high- T_c superconductor $\text{Bi}_2\text{Sr}_{2-x}\text{La}_x\text{CaCu}_2\text{O}_{8+\delta}$ was successfully grown by a traveling solvent floating zone method. The in-plane resistivity ρ_{ab} shows metallic behavior ($d\rho_{ab}/dT > 0$) near room temperature, although the magnitude of the resistivity is far above the Mott limit for metallic conduction. The Hall mobility of the parent insulator does not so much differ from that of an optimally doped sample. These results suggest that the system is not a simple insulator with a well-defined gap, and the hole in the parent insulator is essentially itinerant, as soon as it is doped.

PACS numbers: 74. 25. Fy, 74. 25. Dw, 74. 72. Hs

INTRODUCTION

It is well known that the high T_c superconductivity occurs with doping carriers into the antiferromagnetic (AF) insulator. The AF insulator is quite different from a conventional insulator, and shows various peculiar features. One of the most peculiar features is that in the lightly doped $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ (LSCO) metallic behavior of the in-plane resistivity ρ_{ab} ($d\rho_{ab}/dT > 0$) near room temperature was observed, even though the magnitude of the in-plane resistivity is far above the Mott limit [1]. This metallic behavior is considered to be responsible for the appearance of band dispersion within the Mott-Hubbard gap seen in the angle-resolved photoemission spectroscopy (ARPES) measurement [2]. The electric states of the doped parent insulator, on the other hand, seem to be quite different between LSCO and the Bi-based cuprates. The charge-stripe order is stabilized in LSCO, whereas it is much weaker in the Bi-based cuprates. LSCO has been most frequently used for systematic studies of the heavily underdoped region of the cuprates, because a heavily underdoped sample is easy to synthesize. By contrast, there are only a few reports on the lightly doped $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ [3, 4], because it is difficult to grow high-quality single crystals of lightly doped region. We have previously grown the parent insulator of $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ by flux method, where the trivalent lanthanide, such as Dy and Er, is substituted for divalent Ca [3]. Here, we have successfully grown the parent insulator of $\text{Bi}_2\text{Sr}_{2-x}\text{La}_x\text{CaCu}_2\text{O}_{8+\delta}$ by a traveling solvent floating zone (TSFZ) method.

EXPERIMENTAL

Two crystals of 40% La doped $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ were used in this study. One is a crystal in which all La atoms were substituted for Sr site ($\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$), and the other is a crystal in which La atoms were substituted for Sr and Ca sites ($\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$). They were grown by TSFZ method with a growth velocity of 0.5mm/h in a mixed gas flow of O_2 (20%) and Ar (80%). The starting composition of the feed rods were $\text{Bi}_{2.1}\text{Sr}_{1.1}\text{La}_{0.8}\text{Ca}_{1.0}\text{Cu}_{2.0}\text{O}_{8+\delta}$ for $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$ and $\text{Bi}_{2.1}\text{Sr}_{1.5}\text{La}_{0.8}\text{Ca}_{1.0}\text{Cu}_{2.0}\text{O}_{8+\delta}$ for $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$. Very large single crystals with a size of $2 \times 4 \times 0.1 \text{ mm}^3$ were successfully grown. By energy dispersive x-ray analysis (EDX), the actual compositions were determined to be $\text{Bi}_{2.01}\text{Sr}_{1.11}\text{La}_{0.84}\text{Ca}_{1.00}\text{Cu}_{2.00}\text{O}_{8+\delta}$ for $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$, and $\text{Bi}_{2.04}\text{Sr}_{1.31}\text{La}_{0.86}\text{Ca}_{0.76}\text{Cu}_{2.00}\text{O}_{8+\delta}$ for $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$. In the case of $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$, excess La replaces the Ca site. Figure 1 shows the XRD pattern for the as-grown $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$ single crystal. All the peaks were indexed as (0 0 l) peaks of the Bi-2212 phase with no trace of impurities. The c -axis length was evaluated to be 30.18 Å for $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$, and 30.38 Å for $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$, which is smaller than that of $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ (30.86 Å). This is due to the larger ion radius of the Sr atom (1.13 Å) than that of the La (1.05 Å) and Ca (1.00 Å) atoms. The in-plane resistivity of $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$ was measured using standard four-probe method, whereas the in-plane resistivity of the highly insulating sample $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$ was measured using a two-probe method with constant voltage (where the sample resistance is much higher than

*E-mail address:fujii@htsc.sci.waseda.ac.jp




FIG. 1: X-ray diffraction pattern for (a) as-grown $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$ (b) as-grown $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$ single crystals.

the contact resistance). The voltage for both samples was confirmed to vary linearly with the current in the measured range from 4.2 to 300 K. The thermopower was measured using a steady-state technique from 4.2 to 300 K. The Hall coefficient measurement was done by sweeping the magnetic field which was applied along the c axis ($c \parallel H$) from -7 to 7 T at fixed temperatures. The Hall resistance was confirmed to be linear in magnetic field. The crystals were annealed in the O_2 or Ar atmosphere at 600 °C for 10 h to change the oxygen contents as is similar to $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ [5].

RESULTS AND DISCUSSION

Figure 2 shows the temperature dependence of the in-plane resistivities for $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$ (closed circles) and $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$ (open circles). $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$ shows insulating behavior ($d\rho_{ab}/dT < 0$) in the measured temperature range. The magnitude of the in-plane resistivity at room temperature is about 30 mΩcm for an as-grown sample. It increases to 120 mΩcm by annealing in Ar, which suggests that the carrier concentration decreases with decreasing the oxygen content. $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$ shows metallic behavior ($d\rho_{ab}/dT > 0$) above 150 K, and the magnitude of the in-plane resistivity is about 5 mΩcm at room temperature. In the inset of Fig. 2, the in-plane resistivity of $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$ is plotted in linear scale to see the metallic behavior clearly. Although observed metallic behavior seems to suggest the Boltzmann transport, the magnitude of the in-plane resistivity is far above the Mott limit for metallic conduction, which




FIG. 2: Temperature dependence of the in-plane resistivities ρ_{ab} for $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$ (closed circles) and $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$ (open circles) with various annealing conditions. Inset: ρ_{ab} of $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$ is plotted in linear scale to emphasize metallic behavior.

is quite different from a conventional insulator (usually called as a “bad metal” [6]).

Figure 3 shows the temperature dependence of the in-plane thermopower for $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$ (closed circles) and $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$ (open circles). For both samples, the thermopower decreases with decreasing temperature, which is consistent with our previous results of $\text{Bi}_2\text{Sr}_2\text{RCu}_2\text{O}_{8+\delta}$ ($R=\text{Dy}, \text{Er}$) [7]. The magnitude of the thermopower increases by Ar annealing and decreases by O_2 annealing, which means that the thermopower decreases with increasing oxygen contents. Since the room temperature thermopower is considered to be a universal measure of the doping level [8], this result indicates that the carrier doping is caused by the excess oxygen. Note that the room-temperature thermopower and the magnitude of the in-plane resistivity of $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$ are smaller than those of $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$. Although these two compounds contain approximately the same amount of La ($x \sim 0.8$), the carrier concentration is different. For example, the carrier concentration per Cu p are estimated to be 0.02 for as-grown $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$, and 0.04 for as-grown $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$. One explanation for this is that the substitution of La for Ca site causes a disorder into the CuO_2 plane to make the doped carriers localized. Another explanation is that the amount of the excess oxygen is different.

Figure 4 shows the temperature dependence of the Hall coefficient R_H for as-grown $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$ (closed circles) and as-grown $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$ (open circles). The Hall coefficients monotonically increase with decreasing temperature for both samples. The room temperature carrier concentration is estimated




FIG. 3: Temperature dependence of the thermopower for $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$ (closed circles) and $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$ (open circles) with various annealing conditions.




FIG. 4: Temperature dependence of the Hall coefficient for as-grown $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$ (closed circles) and as-grown $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$ (open circles). Inset: Hall mobility $\mu \equiv R_H/\rho_{ab}$ plotted as a function of temperature.

from the relation $n = (eR_H)^{-1}$ to be $4 \times 10^{20} \text{ cm}^{-3}$ ($p \sim 0.04$) for $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$, and $1 \times 10^{20} \text{ cm}^{-3}$ ($p \sim 0.01$) for $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$, which agree well with the carrier concentration estimated from the room temperature thermopower. The Hall mobility calculated using the Hall coefficient and the resistivity as $\mu \equiv R_H/\rho_{ab}$ is shown in the inset of Fig. 4. It should be emphasized that the mobility is relatively large; the magnitude of which ($2.2 \text{ cm}^2/\text{Vs}$ for $\text{Bi}_2(\text{Sr},\text{La})_2\text{CaCu}_2\text{O}_{8+\delta}$ and $1.8 \text{ cm}^2/\text{Vs}$ for $\text{Bi}_2(\text{Sr},\text{Ca},\text{La})_3\text{Cu}_2\text{O}_{8+\delta}$) is only 5 times smaller than that of $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ ($10 \text{ cm}^2/\text{Vs}$) [9], although the magnitude of the in-plane resistivity of $\text{Bi}_2(\text{Sr},\text{La},\text{Ca})_3\text{Cu}_2\text{O}_{8+\delta}$ is 100 times larger

than that of $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$. In our previous work of the parent insulator $\text{Bi}_2\text{Sr}_2\text{RCu}_2\text{O}_{8+\delta}$ ($R = \text{Dy}, \text{Er}$), the mobility was too small to measure the Hall coefficient precisely [10]. A similar large mobility at 300 K was reported in the lightly doped LSCO, where only 1% of hole doping causes the metallic behavior [1].

In the case of a conventional semiconductor, the mobility does not decrease with decreasing carrier concentration. It is rather possible that the mobility becomes large with decreasing carrier concentration because of the suppression of the electron-electron scattering. While, in the case of the doped antiferromagnetic insulator, such as high- T_c superconductor, the hole is replaced by the spin in the next site whenever it moves. Then, if the hole moves independently, there is the energy loss of the order of the antiferromagnetic correlation energy and the mean free pass becomes as small as the lattice constant. The fact that the mobility of the parent insulator does not so much differ from that of an optimally doped sample does not agree with above simple consideration. It strongly suggests that the doped holes form a charge order, such as charge stripe or phase separation, and move in a group. Thus, the doped hole in the parent insulator is essentially itinerant and shows metallic behavior.

CONCLUSION

In conclusion, we have successfully grown large single crystals of the parent insulator of $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ by substituting La for Sr. With using these crystals, we have measured the in-plane resistivity, thermopower and Hall coefficient along the CuO_2 plane. the in-plane resistivity of the most conducting sample shows metallic behavior above 150 K. Although the magnitude of the in-plane resistivity of the parent insulator is about 100 times larger than that of optimum doped $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$, the mobility is not so much different from that of the superconducting compounds. These results suggest that the system is not a conventional insulator with a well-defined gap, and the hole in the parent insulator is essentially itinerant, as soon as it is doped. Our single crystal shows relatively large mobility compared to Ca-site-substituted single crystals, which indicates a smaller disorder in CuO_2 plane.

-
- [1] Y. Ando, A. N. Lavrov, S. Komiyama, K. Segawa, X. F. Sun; Phys. Rev. Lett. **87** (2001) 017001.
 - [2] T. Yoshida, X. J. Zhou, T. Sasagawa, W. L. Yang, P. V. Bogdanov, A. Lanzara, Z. Hussain, T. Mizokawa, A. Fujimori, H. Eisaki, Z. -X. Shen, T. Kakeshita, S. Uchida; cond-mat/0206469.
 - [3] T. Kitajima, T. Takayanagi, T. Takemura, I. Terasaki; J. Phys. Condens. Matter **11** (1999) 3169.

- [4] C. Kendziora, L. Follo, D. Mandrus, J. Hartge, P. Stephens, L. Mihaly; Phys. Rev. **B45** (1992) 13025.
- [5] T. Watanabe, T. Fujii, A. Matsuda; Phys. Rev. Lett. **79**, 2113 (1997).
- [6] V. J. Emery, S. A. Kivelson; Phys. Rev. Lett. **74**, 3253 (1995).
- [7] T. Takemura, T. Kitajima, T. Sugaya, I. Terasaki; J. Phys. Condens. Matter **12** (2000) 6199.
- [8] S. D. Obertelli, J. R. Cooper, J. L. Tallon; Phys. Rev. **B46** (1992) 14928.
- [9] A. Maeda, M. Hase, I. Tsukada, K. Noda, S. Takebayashi, K. Uchinokura; Phys. Rev. **B41** (1990) 6418.
- [10] T. Takemura, Master thesis 2001, Waseda Univ. (in Japanese).